

Application No. 10/760,039

AMENDMENTS TO THE SPECIFICATIONIn the Specification

Please substitute the following amended paragraph(s) and/or section(s) (deleted matter is shown by strikethrough and added matter is shown by underlining):

Page 3, line 3

X and X' comprise, each independently, an aromatic group such as, for example, a C₆H₅ group.

Page 3, line 16.

The organophotoreceptor may be provided, for example, in the form of a plate, a belt, a flexible belt, a flexible disk, a sheet, a rigid drum, or a sheet around a rigid or compliant drum. In one embodiment, the organophotoreceptor includes: (a) a photoconductive element comprising the charge transport material, the charge generating compound, a second charge transport material, and a polymeric binder; and (b) the electrically conductive substrate.

Page 12, line 5

The electrically insulating substrate may be paper or a film forming polymer such as polyester (e.g., polyethylene terephthalate or polyethylene naphthalate), polyimide, polysulfone, polypropylene, nylon, polyester, polycarbonate, polyvinyl resin, polyvinyl fluoride, polystyrene and the like. Specific examples of polymers for supporting substrates included, for example, polyethersulfone (STABARTM S-100, available from ICI), polyvinyl fluoride (TEDLARTM, available from E.I. DuPont de Nemours & Company), polybisphenol-A polycarbonate

Application No. 10/760,039

(MAKROFOL™, available from Mobay Chemical Company) and amorphous polyethylene terephthalate (MELINAR™, available from ICI Americas, Inc.). The electrically conductive materials may be graphite, dispersed carbon black, iodine, conductive polymers such as polypyrroles and CALGON Calgon® conductive polymer 261 (commercially available from Calgon Corporation, Inc., Pittsburgh, Pa.), metals such as aluminum, titanium, chromium, brass, gold, copper, palladium, nickel, or stainless steel, or metal oxide such as tin oxide or indium oxide. In embodiments of particular interest, the electrically conductive material is aluminum. Generally, the photoconductor substrate has a thickness adequate to provide the required mechanical stability. For example, flexible web substrates generally have a thickness from about 0.01 to about 1 mm, while drum substrates generally have a thickness from about 0.5 mm to about 2 mm.